

FAG




X-life

HCM71910-E-T-P4S-UL-XL

High speed spindle bearing

High speed spindle bearing HCM719...-E,
adjusted, in pairs or sets, contact angle $\alpha = 25^\circ$, with ceramic balls, restricted tolerances

Informacje techniczne



Twoja aktualna wersja produktu

Preload class	L	Preload light
Contact angle	E	Contact angle 25°
Type of Seal	Without	Not sealed
Cage	T	Laminated fabric cage
Tolerance class	P4S	Tolerance class P4S, FAG standard better than P4 to ISO 492:2023
Arrangement bearing set	U	Single bearing

Main Dimensions & Performance Data

d	50 mm	Bore diameter
D	72 mm	Outside diameter
B	12 mm	Width
C _r	12.300 N	Basic dynamic load rating, radial
C _{0r}	6.400 N	Basic static load rating, radial
C _{ur}	520 N	Fatigue load limit, radial
n _G Grease	32.000 1/min	Limiting speed for grease lubrication
n _G Oil	45.000 1/min	Limiting speed for oil lubrication
≈m	107,85 g	Masa



Mounting dimensions

d _a	55 mm	Diameter shaft shoulder
d _a	h12	Diameter shaft shoulder clearance
D _a	67,5 mm	Shoulder diameter outer ring
D _a	H12	Shoulder diameter outer ring clearance
r _a max	0,6 mm	Maximum recess radius
r _{a1} max	0,15 mm	Maximum recess radius
E _{tk} min	57,2 mm	Minimum diameter injection pitch
E _{tk} max	58,9 mm	Maximum diameter injection pitch
E _{tk1} min	54,8 mm	Minimum diameter injection pitch
E _{tk1} max	58,9 mm	Maximum diameter injection pitch
a	20,2 mm	Distance between the apexes of the pressure cones

Dimensions

r _{min}	0,6 mm	Minimum chamfer dimension
r ₁ min	0,3 mm	Minimum chamfer dimension
α	25 °	Contact angle

Temperature range

T _{min}	-30 °C	Operating temperature min.
T _{max}	100 °C	Operating temperature max.



Additional information

F_{VL}	75 N	Preload force light
F_{VM}	196 N	Preload force medium
F_{VH}	407 N	Preload force heavy
K_{aEL}	214 N	Lift-off force light
K_{aEM}	567 N	Lift-off force medium
K_{aEH}	1.194 N	Lift-off force heavy
c_{aL}	88 N/ μ m	Axial rigidity light
c_{aM}	123 N/ μ m	Axial rigidity medium
c_{aH}	161 N/ μ m	Axial rigidity heavy

Właściwości

-  Obciążenie promieniowe
-  Obciążenie osiowe jednokierunkowe
-  Smarowanie smarem
-  Smarowanie olejem
-  Bez uszczelnienia