


FAG

HS7011-C-T-P4S-UL

High speed spindle bearing

High speed spindle bearing HS70...-C, adjusted, in pairs or sets, contact angle $\alpha = 15^\circ$, restricted tolerances

Informacje techniczne





Twoja aktualna wersja produktu

Contact angle	C	Contact angle 15°
Type of Seal	Without	Not sealed
Cage	T	Laminated fabric cage
Tolerance class	P4S	Tolerance class P4S, FAG standard better than P4 to ISO 492:2023
Arrangement bearing set	U	Single bearing
Preload class	L	Preload light

Main Dimensions & Performance Data

d	55 mm	Bore diameter
D	90 mm	Outside diameter
B	18 mm	Width
C _r	17.900 N	Basic dynamic load rating, radial
C _{0r}	11.500 N	Basic static load rating, radial
C _{ur}	1.210 N	Fatigue load limit, radial
n _{G Grease}	22.000 1/min	Limiting speed for grease lubrication
n _{G Oil}	34.000 1/min	Limiting speed for oil lubrication
n _G	34.000 1/min	Limiting speed
≈m	0,391 kg	Masa





Mounting dimensions

d _a	62 mm	Diameter shaft shoulder
d _a	h12	Diameter shaft shoulder clearance
D _a	83 mm	Shoulder diameter outer ring
D _a	H12	Shoulder diameter outer ring clearance
r _a max	1 mm	Maximum recess radius
r _{a1} max	0,6 mm	Maximum recess radius
E _{tk} min	68,5 mm	Minimum diameter injection pitch
E _{tk} max	70,3 mm	Maximum diameter injection pitch
E _{tk1} min	65,9 mm	Minimum diameter injection pitch
E _{tk1} max	70,3 mm	Maximum diameter injection pitch
a	18,7 mm	Distance between the apexes of the pressure cones

Dimensions

r _{min}	1,1 mm	Minimum chamfer dimension
r ₁ min	1,1 mm	Minimum chamfer dimension
α	15 °	Contact angle

Temperature range

T _{min}	-30 °C	Operating temperature min.
T _{max}	100 °C	Operating temperature max.



Additional information

F_{VL}	62 N	Preload force light
F_{VM}	187 N	Preload force medium
F_{VH}	374 N	Preload force heavy
K_{aEL}	187 N	Lift-off force light
K_{aEM}	588 N	Lift-off force medium
K_{aEH}	1.225 N	Lift-off force heavy
c_{aL}	42 N/μm	Axial rigidity light
c_{aM}	67 N/μm	Axial rigidity medium
c_{aH}	91 N/μm	Axial rigidity heavy

Właściwości

-  Obciążenie promieniowe
-  Obciążenie osiowe jednokierunkowe
-  Smarowanie smarem
-  Smarowanie olejem
-  Bez uszczelnienia